

BENT-COLLAR

STUD						
	STD.	MIN				
TD	TL	BL	BD	CD	CT	X
3/8-16	1.375	.625	.331	5/8	.109	5/8

THREADS: Standard thread is UNC-2A (Rolled when possible), other threads are available upon request. Other diameters available upon request.

MATERIAL: LOW CARBON STEEL
 C-0.23% max. P - 0.04% max.
 Mn - 0.90% max. S - 0.05% max.

STAINLESS STEEL
 AISI grade - 302/304/305 std.
 Other grades available upon request.


MECHANICAL PROPERTIES:
 Tensile 60,000 psi (min.)
 Yield 50,000 psi (min.)
 Elongation 20% (in 2 inches)

Values for various grades available upon request.

PLATING: Plating is not standard. Cadmium, Copper, Nickel, and Zinc available upon customer request.

Does not apply to Stainless.

FERRULES: Ferrules are component parts of studs. Not sold separately.



FERRULE					
CODE	B	D	E	M	PART NO.
C375	.785	.875	.125	.250	092 0014 08

TO ORDER OR SPECIFY GIVE:

1. Product Code ARC B-COL
2. Base Diameter BD
3. Base Length BL
4. Thread Diameter TD
5. Thread Length TL
6. Material

NEW-AGE
FASTENING SYSTEMS, INC.

Studwelding Equipment, Fasteners & Supplies
 Boiler Outage Specialists
 Jobsite Studwelding Division
 P.O. Box 5658, Deptford, NJ 08096
 Phone: (856) 218-8301
 Fax: (856) 218-8305
 Toll Free: (888) 889-3833
 steve@newagestudwelding.com

All information contained herein subject to change without notice.