

LONG REDUCED BASE

STUD						
D	MIN		MIN		FH	FERRULE CODE
	L	BD	BL	FD		
1/4	3/4	.187	.375	.281	.109	FS187
5/16	3/4	.250	.375	.359	.125	FS250
3/8	3/4	.312	.375	.437	.125	FS312
7/16	1	.375	.375	.500	.140	FS375
1/2	1	.437	.437	.578	.140	FS437
5/8	1-1/4	.500	.500	.656	.156	FS500
3/4	1-1/2	.625	.718			FS625


THREADS: Standard thread is UNC-2A (Rolled when possible), other threads are available upon request. Maximum standard thread length is 3-7/8".

MATERIAL:	LOW CARBON STEEL	STAINLESS STEEL
	C-0.23% max. P-0.04% max. Mn-0.90% max. S-0.05% max.	AISI grade - 302/304/305 std. Other grades available upon request.

MECHANICAL PROPERTIES:	Tensile	60,000 psi (min.)	Values for various grades available upon request.
	Yield	50,000 psi (min.)	
Elongation	20% (in 2 inches)		

PLATING:	Plating is not standard. Cadmium, copper nickel, and zinc available upon customer request.	Does not apply to Stainless.
-----------------	--	------------------------------

FERRULES: Ferrules are component parts of studs. Not sold separately.



FERRULE					
CODE	B	D	E	M	PART NO.
FS187	.305	.390	.125	.250	092 0004 05
FS250	.380	.455	.125	.250	092 0004 06
FS312	.505	.595	.125	.250	092 0004 07
FS375	.585	.675	.125	.250	092 0004 08
FS437	.650	.740	.156	.281	092 0004 09
FS500	.785	.875	.156	.281	092 0004 10
FS625	.921	1.030	.187	.375	092 0004 11

TO ORDER OR SPECIFY GIVE:

1. Product Code ARC LRB
2. Diameter D
3. Length L
4. Material

NEW-AGE FASTENING SYSTEMS, INC.

Studwelding Equipment, Fasteners & Supplies
 Boiler Outage Specialists
 Jobsite Studwelding Division
 P.O. Box 5658, Deptford, NJ 08096
 Phone: (856) 218-8301
 Fax: (856) 218-8305
 Toll Free: (888) 889-3833
 steve@newagestudwelding.com

All information contained herein subject to change without notice.