


## DRAWN ARC - NO THREAD



STUD		
		MIN
D	FD	L
.115	3/32	.250
		.250
.141	1/8	.250
		.250
.161	5/32	.250
		.250
.215	3/16	.250
		.312
	1/4	.312

<b>MATERIAL:</b> LOW CARBON STEEL C - 0.23% max. P - 0.04% max. Mn - 0.90% max. S - 0.05% max.	<b>STAINLESS STEEL</b> AISI grade - 302/304/305 std. Other grades available upon request.
<b>MECHANICAL PROPERTIES:</b> Tensile 60,000 psi (min.) Yield 50,000 psi (min.) Elongation 20% (in 2 inches)	Values for various grades available upon request.
<b>PLATING:</b> Copper plating is standard.	Does not apply to Stainless
<b>ANNEALING:</b> Studs are annealed where required.	Studs are annealed where required.
<b>MATERIAL:</b> ALUMINUM Alloy — 1100 & 5000 series Other alloys available upon request.	<b>BRASS</b> Alloy — (lead free) 70-30 std. Other alloys available upon request.
<b>MECHANICAL PROPERTIES:</b> Values for various alloys available upon request.	Values for various alloys available upon request.

**TO ORDER OR SPECIFY GIVE:**

1. Product Code . . . . . CD DA-NT
2. Diameter . . . . . D
3. Length . . . . . L
4. Material . . . . .

**NEW-AGE**  
**FASTENING SYSTEMS, INC.**

Studwelding Equipment, Fasteners & Supplies  
Boiler Outage Specialists  
Jobsite Studwelding Division  
P.O. Box 5650, Deptford, NJ 08096  
Phone: (856) 218-8301  
Fax: (856) 218-8305  
Toll Free: (888) 889-3833  
steve@newagestudwelding.com

All information contained herein subject to change without notice.