


DRAWN ARC



STUD		
<i>D</i>	<i>FD</i>	<i>MIN L</i>
4-40	.143	.250
6-32	.169	.250
8-32	.195	.250
10-32	.221	.250
10-24	.221	.250
1/4-20	.281	.375

MATERIAL: LOW CARBON STEEL C - 0.23% max. P - 0.04% max. Mn - 0.90% max. S - 0.05% max.	STAINLESS STEEL AISI grade - 302/304/305 std. Other grades available upon request.
MECHANICAL PROPERTIES: Tensile 60,000 psi (min.) Yield 50,000 psi (min.) Elongation 20% (in 2 inches)	Values for various grades available upon request.
PLATING: Copper coating is standard.	Does not apply to Stainless
ANNEALING: Studs are annealed where required.	Studs are annealed where required.
MATERIAL: ALUMINUM Alloy — 1100 & 5000 series std. Other alloys available upon request.	BRASS Alloy — (lead free) 70-30 std. Other alloys available upon request.
MECHANICAL PROPERTIES: Values for various alloys available upon request.	Values for various alloys available upon request.

TO ORDER OR SPECIFY GIVE:

- | | |
|---------------------------|-------|
| 1. Product Code | CD DA |
| 2. Diameter | D |
| 3. Length | L |
| 4. Material | |

NEW-AGE
FASTENING SYSTEMS, INC.

Studwelding Equipment, Fasteners & Supplies
Boiler Outage Specialists
Jobsite Studwelding Division
P.O. Box 5658, Deptford, NJ 08096
Phone: (856) 218-8301
Fax: (856) 218-8305
Toll Free: (888) 889-3833
steve@newagestudwelding.com

All information contained herein subject to change without notice.