

COLLAR

TD	STUD						FERRULE CODE
	MIN TL	BD	MIN BL	CD	CT		
1/4	.375	.215	.500	.500	.093	C250	
5/16	.375	.275	.500	.562	.093	C312	
3/8	.500	.330	.500	.625	.109	C375	
1/2	.625	.448	.593	.750	.140	C500	

THREADS: Standard thread is UNC-2A (Rolled when possible), other threads are available upon request. Maximum standard thread length is 3-7/8".

MATERIAL: LOW CARBON STEEL
C - 0.23% max. P - 0.04% max.
Mn - 0.90% max. S - 0.05% max.

STAINLESS STEEL
AISI grade - 302/304/305 std.
Other grades available upon request.


MECHANICAL PROPERTIES:
Tensile 60,000 psi (min.)
Yield 50,000 psi (min.)
Elongation 20% (in 2 inches)

Values for various grades available upon request.

PLATING: Plating is not standard. Cadmium, Copper, Nickel, and Zinc available upon customer request.

Does not apply to Stainless.

FERRULES: Ferrules are component parts of studs. Not sold separately.



CODE	FERRULE					PART NO.
	B	D	E	M		
C250	.785	.875	.125	.250	092 0014 06	
C312	.785	.875	.125	.250	092 0014 07	
C375	.785	.875	.125	.250	092 0014 08	
C500	1.030	1.203	.125	.281	092 0014 10	

TO ORDER OR SPECIFY GIVE:

1. Product Code ARC COL
2. Base Diameter BD
3. Base Length BL
4. Thread Diameter TD
5. Thread Length TL
6. Material

NEW-AGE
FASTENING SYSTEMS, INC.

Studwelding Equipment, Fasteners & Supplies
Boiler Outage Specialists
Jobsite Studwelding Division
P.O. Box 5658, Deptford, NJ 08096
Phone: (856) 218-8301
Fax: (856) 218-8305
Toll Free: (888) 889-3833
steve@newagestudwelding.com

All information contained herein subject to change without notice.