


## FLANGED



STUD		
<i>D</i>	<i>FD</i>	<i>MIN L</i>
2-56	.156	.250
4-40	.187	.250
6-32	.218	.250
8-32	.250	.250
10-32	.250	.250
10-24	.250	.250
1/4-20	.312	.375
5/16-18	.375	.500

<b>MATERIAL: LOW CARBON STEEL</b> C - 0.23% max. P - 0.04% max. Mn - 0.90% max. S - 0.05% max.	<b>STAINLESS STEEL</b> AISI grade - 302/304/305 std. Other grades available upon request.
<b>MECHANICAL PROPERTIES:</b> Tensile 60,000 psi (min.) Yield 50,000 psi (min.) Elongation 20% (in 2 inches)	Values for various grades available upon request.
<b>PLATING:</b> Copper coating is standard.	Does not apply to Stainless
<b>ANNEALING:</b> Studs are annealed where required.	Studs are annealed where required.
<b>MATERIAL: ALUMINUM</b> Alloy — 1100 & 5000 series Other alloys available upon request.	<b>BRASS</b> Alloy — (lead free) 70-30 std. Other alloys available upon request.
<b>MECHANICAL PROPERTIES:</b> Values for various alloys available upon request.	Values for various alloys available upon request.

**TO ORDER OR SPECIFY GIVE:**

- |                       |      |
|-----------------------|------|
| 1. Product Code ..... | CD F |
| 2. Diameter .....     | D    |
| 3. Length .....       | L    |
| 4. Material .....     |      |

**NEW-AGE**  
**FASTENING SYSTEMS, INC.**

Studwelding Equipment, Fasteners & Supplies  
Boiler Outage Specialists  
Jobsite Studwelding Division  
P.O. Box 5658, Deptford, NJ 08096  
Phone: (856) 218-8301  
Fax: (856) 218-8305  
Toll Free: (888) 889-3833  
steve@newagesstudwelding.com

All information contained herein subject to change without notice.